

## TEHNIČKE KARAKTERISTIKE

technical specification

### Testliner bijeli / white PANLINER

<b>GRAMATURA</b> grammage g/m <sup>2</sup> ISO 536	0	125 ± 3%	130 ± 3%	135 ± 3%	140 ± 3%	145 ± 3%	150 ± 3%	160 ± 3%	165 ± 3%	170 ± 3%
<b>VLAGA</b> moisture content % ISO 20287	0	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5
<b>MULLEN</b> bursting strenght kPa ISO 2758	0	300 ± 5%	310 ± 5%	320 ± 5%	330 ± 5%	340 ± 5%	350 ± 5%	360 ± 5%	380 ± 5%	390 ± 5%
<b>SCT</b> quer compressive strength CD kN/m ISO 9895	0	2,14 ± 5%	2,22 ± 5%	2,27 ± 5%	2,37 ± 5%	2,42 ± 5%	2,48 ± 5%	2,58 ± 5%	2,63 ± 5%	2,68 ± 5%
<b>BJELOĆA</b> whiteness	0	68-69%	68-69%	68-69%	68-69%	68-69%	68-69%	68-69%	68-69%	68-69%
<b>Cobb</b> 60-test g/m <sup>2</sup> ISO 20535	max	40	40	40	40	40	40	40	40	40

Uvjeti ispitivanja / test condition: 23°C, 50% r.v.