

## TEHNIČKE KARAKTERISTIKE

technical specification

### Testliner 3 smeđi / braun PANLINER 3 B

<b>GRAMATURA</b> grammage g/m <sup>2</sup> ISO 536	0	110 ± 3%	115 ± 3%	120 ± 3%	125 ± 3%	130 ± 3%	135 ± 3%	140 ± 3%	145 ± 3%	150 ± 3%	160 ± 3%	165 ± 3%	170 ± 3%
<b>VLAGA</b> moisture content % ISO 20287	0	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5	7,5 ± 1,5
<b>MULLEN</b> bursting strenght kPa ISO 2758	0	270 ± 5%	280 ± 5%	300 ± 5%	310 ± 5%	320 ± 5%	330 ± 5%	340 ± 5%	350 ± 5%	360 ± 5%	370 ± 5%	390 ± 5%	400 ± 5%
<b>SCT</b> quer compressive strength CD kN/m ISO 9895	0	1,85 ± 5%	2,01 ± 5%	2,16 ± 5%	2,24 ± 5%	2,32 ± 5%	2,37 ± 5%	2,47 ± 5%	2,52 ± 5%	2,58 ± 5%	2,68 ± 5%	2,73 ± 5%	2,78 ± 5%
<b>Cobb</b> 60-test g/m <sup>2</sup> ISO 20535	max	40	40	40	40	40	40	40	40	40	40	40	40

Uvjeti ispitivanja / test condition: 23°C, 50% r.v.