

## Technical specification of pulp, which is better than pulp from wood

Sample	Parameter	Units	Measured value
PS-14-16-1 Grounded, whitened	Grammage	g/m <sup>2</sup>	96,11
	Breaking length	km	6,100
	Tear Index	kPam <sup>2</sup> /g	3,50
	Opacity	%	83,40
	ISO brightness	%	97,66
	CMT <sub>0</sub>	N	180,3
	CMT <sub>30</sub>	N	145,9
PS-14-16-2 ungrounded, whitened	Lignin content	%	4,8
	Grammage	g/m <sup>2</sup>	100,92
	Breaking length	km	5,410
	Tear Index	kPam <sup>2</sup> /g	3,25
	Opacity	%	85,13
	ISO brightness	%	97,94
	CMT <sub>0</sub>	N	188,8
	CMT <sub>30</sub>	N	150,2